

Document
Title:

GL300 SUC 05/07 S4Wa



Document
Type:

Product Specification

General Information:

Temperature: R.T.I. 150°C
Max 250°C
Shelf Life: 3 months at 15°C wrapped as supplied
Nom finished thickness: 0.55mm

Nominal Fabric Details:

Designation: Dawson GL300
Type: Glass fibre, plain weave.
Tensile: Warp 740 N/cm min
Weft 500 N/cm min
Thickness: 0.25mm
Weight: 290 g/m²

Silicone Specification:

Designation: S4Wa
Hardness: 70° IRHD
Specific Gravity: 1.15 g/cm³
Typical Dielectric Strength: 20 kV/mm (1mm sample)
Typical Thermal Expansion: 8.2 x 10⁻⁴/°C linear

Packing Details:

Protected one side with polythene film. Packed in cardboard cartons supported on central tube.

Any data contained herein relates only to this report and should not be used to compile any specifications.

Date:	15/04/2004	Issue:	1
Released:	R Turner	Approved:	K Walker
			Page 1 of 1